



Customized Adhesive Solutions

25 B Street, Burlington, MA 01803

Phone: (978) 436-9600 Fax: (866) 788-7856

Email: info@nextgenadhesives.com

NGAC G907-68

Technical Bulletin

Thixotropic Casting Epoxy Adhesive

Description:

NGAC G907-68 is a thixotropic casting adhesive formulated with a high fill to provide non-sag for applications such as coil repair.

Advantages and Applications:

The NGAC G907-68 provides excellent chemical, mechanical resistance, as well as, overall toughness. The NGAC G907-68 is easily mixed and cured at room temperature and provides excellent adhesion to glass, ceramic, metal and plastic

NGAC G907-68 features the following characteristics that enable ease of use.

Properties:

	Typical Value
Color	Dark Red
Specific Gravity	1.24
Mixed Viscosity	28,000 cps
Mix Ratio by Weight (R/H)	100/22
Hardness Shore D	90
Dielectric Constant, 1KHz@25C	4.20
Dielectric Strength	400 Volts/Mil
Operating Temperature:	-65 to 120°C
Pot Life	30 Min

Cure Schedule:

Temperature	25C	65C
Time	24	4 hours

For additional information or assistance, please call **978-436-9600**

All values reported above are typical values and are for reference use only. These values are not intended for use in developing specifications. Application testing under specific conditions should be performed to determine actual results and fitness for use.